



ENDUTEX - REVESTIMENTOS TEXTEIS, SA

VIZELA / PORTUGAL



TECHNICAL INFORMATION

REFERENCE: RECYTEX F300 FR

DESCRIPTION: HIGH TENACITY POLYPROPYLENE FABRIC COATED WITH POLYOLEFINS ⁽¹⁾

AVAILABLE WIDTHS: Up to 500 cm


THICKNESS (mm)		0,42
TOTAL MASS (g/m ²)		300
FABRIC MASS (g/m ²)		140
MECHANICAL PROPERTIES (Comparable to PVC coated fabrics)	Breaking Load (daN/50mm)	L: 175 T: 118
	Trapezoidal Tear Strength (daN)	L: 25 T: 16
SERVICE TEMPERATURE RANGE		-15°C to 70°C
WELDABILITY		Hot air
INK COMPATIBILITY ⁽²⁾		Solvent, Eco-Solvent, Latex ⁽³⁾ and UV Inks

(1) **Patent Pending**

(2) No need for any additional surface treatment

(3) Profile available. For more information, please contact endutex@endutex.pt.

RECYCLABILITY

International code		
Information for reprocessing	Extrusion details (Processing temperature range)	165°C to 180°C (T _{die} ≈ 175°C)
	Injection Moulding details (Processing temperature range)	165°C to 190°C (T _{inj} ≈ 185°C)